

Chemical Resistance Chart

7430 series (57040)

Aromatic Urethane

Rating Key: 0 = No Effect; 1 = Not Recommended; 3 = Etches and Softens Surface (Immersion/Splash or Spill)
Ratings are based on 7-day spot test.

Chemical	Rating	Chemical	Rating
Acetic Acid (5%)	1/0	Methyl Alcohol	1/0
Acetic Acid (20%)	1/0	Methyl Ethyl Ketone	1/0
Acetic Acid (100%)	1/1	Methylisobutyl Ketone	1/0
Ammonium Hydroxide (10%)	0/0	Mineral Spirits	0/0
Calcium Chloride in Water (20%)	0/0	Motor Oil	0/0
Carbon Tetrachloride	0/0	Nitric Acid (5%)	1/0
Cellosolve Acetate	1/0	Nitric Acid (10%)	1/0
Ethyl Alcohol	1/0	Sodium Chloride in Water (20%)	0/0
Ethylene Glycol (Antifreeze)	0/0	Sodium Hydroxide (50%)	0/0
Fatty Acids (100%)	1/0	Sodium Hypochlorite (12%)	1/2
Gasoline	0/0	Sulfuric Acid (5%)	0/0
Glycerine	0/0	Sulfuric Acid (10%)	1/0
Hydraulic Fluid	0/0	Sulfuric Acid (25%)	1/0
Hydrochloric Acid (5%)	1/0	Sulfuric Acid (50%)	1/1
Hydrochloric Acid (10%)	1/0	Toluene	1/0
Hydrochloric Acid (20%)	1/0	Trichloroethane	1/0
Hydrochloric Acid (37%)	1/0	Xylene	1/0

Issued by: Hempel (USA) – 7430 series CRC

This document is intended for professional use and provides generic advice in respect of the subject matter hereof only. It is not intended to be used as a comprehensive guide. The buyer/applicator should always read the relevant Product Data Sheets ("PDS"), Safety Data Sheets and Guide Specification relating to the applicable products/system. If in doubt, please contact your local Neogard representative for further advice. To the extent relevant, the disclaimer set forth in the relevant PDS or Guide Specification applies to this document. 7430-CRC ksk 09022021.docx