

# Chemical Resistance Chart

FC7530/FC7963 (57060)

Aliphatic Urethane



Rating Key: 0 = No Effect; 1 = Stains/Dulls Film; 2 = Blisters Film; 3 = Lifts Film  
Ratings are based on 7-day spot test.

Chemical	Rating	Chemical	Rating
Bleach	2	Sodium Hydroxide, 10%	0
Ethylene Glycol	0	Sodium Hydroxide, 20%	0
Gasoline	2	Sulfuric Acid, 20%	0
Hydrochloric Acid, 10%	0		

Issued by: Hempel (USA) – FC7530/FC7963 CRC

This document is intended for professional use and provides generic advice in respect of the subject matter hereof only. It is not intended to be used as a comprehensive guide. The buyer/applicator should always read the relevant Product Data Sheets ("PDS"), Safety Data Sheets and Guide Specification relating to the applicable products/system. If in doubt, please contact your local Neogard representative for further advice. To the extent relevant, the disclaimer set forth in the relevant PDS or Guide Specification applies to this document. FC7530-FC7963-CRC ksk 09022021.docx

Neogard®, A part of Hempel  
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com