

AutoGard FC

Table of Contents

FC7510/FC7961 Chemical Resistance Chart	Technical Bulletins	English	2
FC7540/FC7964 Chemical Resistance Chart	Technical Bulletins	English	3

Chemical Resistance Chart

FC7510/FC7961 (47PJB)

Aromatic Urethane

Rating Key: 0 = No Effect; 1 = Stains/Dulls Film; 2 = Blisters Film; 3 = Lifts Film
Ratings are based on 7-day spot test.

Chemical	Rating	Chemical	Rating
Ammonia (28%)	0	Nitric Acid (5%)	1
Bleach	1	Oleic Acid	0
Brake Fluid	2	Phosphoric Acid (10%)	1
Calcium Chloride (10%)	0	Propylene Glycol	0
Ethylene Glycol	0	Sodium Hypochlorite (10%)	0
Hydrochloric Acid (5%)	0	Sodium Hydroxide (20%)	0
Hydrochloric Acid (15%)	0	Sodium Hydroxide (50%)	0
Isopropyl Alcohol	0	Soya Oil	0
Jet Fuel	0	Sulfuric Acid (5%)	0
Gasoline	0	Sulfuric Acid (10%)	0
Mineral Spirits	0	Sulfuric Acid (20%)	0
Motor Oil	0	Tall Oil Fatty Acid	0

Issued by: Hempel (USA) – FC7510/FC7961 CRC

This document is intended for professional use and provides generic advice in respect of the subject matter hereof only. It is not intended to be used as a comprehensive guide. The buyer/applicator should always read the relevant Product Data Sheets ("PDS"), Safety Data Sheets and Guide Specification relating to the applicable products/system. If in doubt, please contact your local Neogard representative for further advice. To the extent relevant, the disclaimer set forth in the relevant PDS or Guide Specification applies to this document. FC7510-FC7961-CRC ksk 09022021.docx

Neogard®, A part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com

Chemical Resistance Chart

FC7540/FC7964 (47QJB)

Aliphatic Urethane

Rating Key: 0 = No Effect; 1 = Stains/Dulls Film; 2 = Blisters Film; 3 = Lifts Film
Ratings are based on 7-day spot test.

Chemical	Rating	Chemical	Rating
Ammonia (28%)	0	Oleic Acid	1
Bleach	1	Phosphoric Acid (10%)	1
Brake Fluid	2	Propylene Glycol	0
Calcium Chloride (10%)	0	Sodium Hydroxide (20%)	1
Ethylene Glycol	0	Sodium Hydroxide (50%)	1
Gasoline	0	Sodium Hypochlorite (10%)	1
Hydrochloric Acid (5%)	1	Soya Oil	1
Hydrochloric Acid (15%)	1	Sulfuric Acid (5%)	1
Isopropyl Alcohol	1	Sulfuric Acid (10%)	1
Jet Fuel	0	Sulfuric Acid (20%)	1
Mineral Spirits	0	Tall Oil Fatty Acid	2
Motor Oil	0	Transmission Oil	1
Nitric Acid (5%)	1		

Issued by: Hempel (USA) – FC7540/FC7964 CRC

This document is intended for professional use and provides generic advice in respect of the subject matter hereof only. It is not intended to be used as a comprehensive guide. The buyer/applicator should always read the relevant Product Data Sheets ("PDS"), Safety Data Sheets and Guide Specification relating to the applicable products/system. If in doubt, please contact your local Neogard representative for further advice. To the extent relevant, the disclaimer set forth in the relevant PDS or Guide Specification applies to this document. FC7540-FC7964-CRC ksk 09022021.docx

Neogard®, A part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com