

Neocrete

Table of Contents

70704/70705 Chemical Resistance Chart	Technical Bulletins	English	2
70817 - 70817-01/70818 Chemical Resistance Chart	Technical Bulletins	English	4
70869/70819 Chemical Resistance Chart	Technical Bulletins	English	6
Neocrete Chemical Resistance Chart	Technical Bulletins	English	7

Chemical Resistance Chart

70704/70705 (45020)

Novolac Epoxy

Rating Key: 0 = No Effect; 1 = Stains/Dulls Film; 2 = Blisters Film; 3 = Lifts Film
Ratings are based on 7-day spot test.

Chemical	Rating	Chemical	Rating
Acetic Acid (10%)	0-1	Jet Fuel	0
Acetic Acid (20%)	0-1	Ketchup	0
Acetic Acid (36%)	0-1	Lactic Acid (20%)	0-1
Acetic Acid (98%)	0-1	Lactic Acid (50%)	0-1
Ammonia (28%)	0	Lactic Acid (85%)	0-1
Blood	0	Methylisobutyl Ketone	0
Brake Fluid	0	Methylpyrrolidione	0
Butoxyethanol	0	Mineral Spirits	0
Butoxyethylacetate	1-2	Motor Oil	0
Butyl Alcohol	0	Mustard	1
Butylacrylate	0	Nitric Acid (10%)	1
Calcium Chloride (10%)	0	Nitric Acid (30%)	1
Chromic Acid (2%)	1	Oleic Acid	0
Citric Acid (6%)	0	Phenol	1
Citric Acid (25%)	0	Phosphoric Acid (25%)	1
Citric Acid (50%)	0	Potassium Hydroxide (25%)	0
Citric Acid (70%)	0	Propylene Glycol	0
Diacetone Alcohol	0	Skydrol	0
Diesel Fuel	0	Sodium Hydroxide (25%)	0
Ethyl Acetate	0	Sodium Hydroxide (50%)	0
Ethyl Alcohol	0	Sodium Hypochlorite (10%)	0
Ethylene Glycol	0	Solvent 100	0
Formic Acid (38%)	1	Sulfuric Acid (10%)	1
Gasoline	0	Sulfuric Acid (20%)	1
Hydrobromic (48%)	1	Sulfuric Acid (50%)	1
Hydrochloric Acid (5%)	0	Sulfuric Acid (96%)	0-1
Hydrochloric Acid (15%)	0	Tall Oil Fatty Acid	0
Hydrochloric Acid (37%)	0	Urine	0
Hydrofluoric Acid (24%)	0-1	Vegetable Oil	0
Hydrofluoric Acid (48%)	0-1	Vinegar	0
Isopropyl Alcohol	0	Xylene	0

Chemical Resistance Chart

70704/70705 (45020)

Novolac Epoxy

Issued by: Hempel (USA) – 70704/70705 CRC

This document is intended for professional use and provides generic advice in respect of the subject matter hereof only. It is not intended to be used as a comprehensive guide. The buyer/applicator should always read the relevant Product Data Sheets ("PDS"), Safety Data Sheets and Guide Specification relating to the applicable products/system. If in doubt, please contact your local Neogard representative for further advice. To the extent relevant, the disclaimer set forth in the relevant PDS or Guide Specification applies to this document. 70704-70705-CRC ksk 09022021.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com

Chemical Resistance Chart

70817/70818 and 70817-01/70818 (57070)

Chemical Resistant Urethane

Rating Key: 0 = No Effect; 1 = Stains/Dulls Film; 2 = Blisters Film; 3 = Lifts Film

Ratings are based on 7-day spot test.

Note: Staining is possible with mustard and urine on white and clear systems.

Chemical	Rating	Chemical	Rating
Acetic Acid (10%)	0	Hydrochloric Acid (5%)	0
Acetic Acid (20%)	0	Hydrochloric Acid (15%)	0-1
Acetic Acid (36%)	0	Hydrofluoric Acid (24%)	0-1
Acetic Acid (98%)	1-2	Hydrochloric Acid (37%)	1
Ammonia (28%)	0	Hydrofluoric Acid (48%)	0-1
Blood	0	Methylisobutyl Ketone	0
Brake Fluid	0-1	Methylpyrrolidione	1-2
Butoxyethanol	0-1	Mineral Spirits	0
Butoxyethylacetate	0-1	Motor Oil	0
Butyl Alcohol	0	Mustard	1
Butylacrylate	0	Nitric Acid (10%)	0-1
Calcium Chloride (10%)	0	Nitric Acid (30%)	0-1
Chromic Acid (2%)	0-1	Oleic Acid	0-1
Citric Acid (25%)	0	Phenol	1
Citric Acid (50%)	0	Phosphoric Acid (25%)	1
Citric Acid (6%)	0	Potassium Hydroxide (25%)	0-1
Citric Acid (70%)	0	Propylene Glycol	0
Diacetone Alcohol	0-1	Skydrol	0
Diesel Fuel	0	Sodium Hydroxide (25%)	0-1
Ethyl Acetate	1	Sodium Hydroxide (50%)	1
Ethyl Alcohol	0	Sodium Hypochlorite (10%)	0-1
Ethylene Glycol	0	Solvent 100	0-1
Formic Acid (38%)	1	Sulfuric Acid (10%)	0-1
Gasoline	0	Sulfuric Acid (50%)	1
Hydrobromic (48%)	1	Sulfuric Acid (96%)	2
Isopropyl Alcohol	0	Tall Oil Fatty Acid	0
Jet Fuel	0	Transmission Oil	0
Ketchup	0	Urine	0
Lactic Acid (20%)	0-1	Vegetable Oil	0
Lactic Acid (50%)	1-2	Vinegar	0
Lactic Acid (85%)	1-2	Xylene	0

Chemical Resistance Chart

70817/70818 and 70817-01/70818 (57070)

Chemical Resistant Urethane

Issued by: Hempel (USA) – 70817/70718 & 70817-01/70718 CRC

This document is intended for professional use and provides generic advice in respect of the subject matter hereof only. It is not intended to be used as a comprehensive guide. The buyer/applicator should always read the relevant Product Data Sheets ("PDS"), Safety Data Sheets and Guide Specification relating to the applicable products/system. If in doubt, please contact your local Neogard representative for further advice. To the extent relevant, the disclaimer set forth in the relevant PDS or Guide Specification applies to this document. 70817-70817-01-70818-CRC ksk 09022021.docx

Neogard®, a part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com

Chemical Resistance Chart

70869/70819 Polyaspartic, Clear (5703100050)

70869-01/70819 Polyaspartic, White (5703200010)

Rating Key: 0 = No Effect; 1 = Stains/Dulls Film; 2 = Blisters Film; 3 = Lifts Film
Ratings are based on 7-day spot test.

70869/70819 Polyaspartic, Clear (5703100050)		70869-01/70819 Polyaspartic, White (5703200010)	
Chemical	Rating	Chemical	Rating
Acetic Acid 36%	1	Acetic Acid 36%	1
Auto Transmission Fluid	0	Auto Transmission Fluid	0
Brake Fluid	1	Brake Fluid	2
Butoxy Ethanol	2	Butoxy Ethanol	1
Diesel Fuel	1	Diesel Fuel	1
Hydrochloric Acid 15%	1	Hydrochloric Acid 15%	1
Hydrochloric Acid 37%	1	Hydrochloric Acid 37%	1
Lactic Acid 20%	1	Lactic Acid 20%	2
Lactic Acid 85%	2	Lactic Acid 85%	2
Methyl Isobutyl Ketone (MIBK)	1	Methyl Isobutyl Ketone (MIBK)	1
Nitric Acid	0	Nitric Acid	1
Skydrol	2	Skydrol	2
Sodium Hydroxide 50%	1	Sodium Hydroxide 50%	0
Sulfuric Acid 10%	0	Sulfuric Acid 10%	1

Issued by: Hempel (USA) – 70869/70819 & 70869-01/70819 CRC

This document is intended for professional use and provides generic advice in respect of the subject matter hereof only. It is not intended to be used as a comprehensive guide. The buyer/applicator should always read the relevant Product Data Sheets ("PDS"), Safety Data Sheets and Guide Specification relating to the applicable products/system. If in doubt, please contact your local Neogard representative for further advice. To the extent relevant, the disclaimer set forth in the relevant PDS or Guide Specification applies to this document. 70869-70819-CRC ksk 09022021.docx

Chemical Resistance Chart

Neocrete Products:

RT (48021), SL (48012), Trowel (48010), V (48011)

Rating Key: 0 = No Effect; 1 = Stains/Dulls Film; 2 = Blisters Film; 3 = Lifts Film
Ratings are based on 7-day spot test.

Chemical	Rating	Chemical	Rating
Acetic Acid (10%)	1	Jet Fuel	0
Acetic Acid (20%)	1	Ketchup	0
Acetic Acid (36%)	1	Lactic Acid (20%)	0
Acetic Acid (98%)	1	Lactic Acid (50%)	1
Ammonia (28%)	0	Lactic Acid (85%)	1
Antifreeze (220°F)	0	Methylisobutyl Ketone	0
Betadine	0	Methylpyrrolidone	1
Bleach	0	Mineral Spirits	0
Blood	0	Motor Oil	0
Brake Fluid	1	Mustard	1
Brake Fluid (220°F)	1	Nitric Acid (10%)	1
Butoxyethanol	0	Nitric Acid (30%)	1
Butoxyethylacetate	0	Oleic Acid	1
Butyl Alcohol	0	Phenol	1
Butylacrylate	0	Phosphoric Acid (25%)	1
Calcium Chloride (10%)	0	Potassium Hydroxide (25%)	0
Citric Acid (6%)	0	Propylene Glycol	0
Citric Acid (25%)	0	Skydrol	1
Citric Acid (50%)	0	Sodium Hydroxide (25%)	0
Citric Acid (70%)	0	Sodium Hydroxide (50%)	0
Diacetone Alcohol	0	Sodium Hypochlorite (10%)	1
Diesel Fuel	0	Solvent 100	0
Diesel Fuel (220°F)	0	Soy Oil (500°F)	0
Ethyl Acetate	0	Sulfuric Acid (10%)	1
Ethyl Alcohol	0	Sulfuric Acid (20%)	1
Ethylene Glycol	0	Sulfuric Acid (50%)	1
Formic Acid (38%)	1	Sulfuric Acid (96%)	3
Gasoline	0	Tall Oil Fatty Acid	1
Hydrobromic Acid (48%)	1	Transmission Fluid (220°F)	0
Hydrochloric Acid (5%)	1	Urine	1
Hydrochloric Acid (15%)	1	Vegetable Oil	0
Hydrochloric Acid (37%)	1	Vinegar	1
Isopropyl Alcohol	0	Xylene	0

Chemical Resistance Chart

Neocrete Products:

RT (48021), SL (48012), Trowel (48010), V (48011)



Issued by: Hempel (USA) – Neocrete Products CRC

This document is intended for professional use and provides generic advice in respect of the subject matter hereof only. It is not intended to be used as a comprehensive guide. The buyer/applicator should always read the relevant Product Data Sheets ("PDS"), Safety Data Sheets and Guide Specification relating to the applicable products/system. If in doubt, please contact your local Neogard representative for further advice. To the extent relevant, the disclaimer set forth in the relevant PDS or Guide Specification applies to this document. Neocrete-CRC ksk 09022021.docx

Neogard®, A part of Hempel
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com